

KetaSpire® KT-820FP

polyetheretherketone

KetaSpire® KT-820FP is the low-flow grade of unreinforced polyetheretherketone (PEEK) supplied in a natural-color fine powder form suitable for compression molding.

These properties make it well-suited for applications in healthcare, transportation, electronics, chemical processing, and other industrial uses.

KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent wear resistance, best-in-class fatigue resistance, ease of melt processing, high purity, and excellent chemical resistance to organics, acids, and bases.

The resin is also available as KetaSpire® KT-820 NT in a natural-color pellet form for injection molding and extrusion.

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Chemical Resistant • Ductile • Fatigue Resistant • Flame Retardant	• Good Dimensional Stability • Good Impact Resistance • High Heat Resistance
Uses	• Electrical/Electronic Applications • Industrial Applications	• Oil/Gas Applications
Agency Ratings	• ISO 10993	
RoHS Compliance	• Contact Manufacturer	
Appearance	• Natural Color	
Forms	• Powder	
Processing Method	• Compression Molding	

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.30		ASTM D792
Water Absorption (24 hr)	0.10	%	ASTM D570
Particle Size			
Retained on 100 mesh sieve	< 0.00	%	
Retained on 140 mesh sieve	< 2.00	%	

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus	3650	MPa	ASTM D638
Tensile Strength	96.5	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	5.2	%	
Break ¹	> 60	%	
Break ²	20 to 30	%	
Flexural Modulus	3860	MPa	ASTM D790
Flexural Strength	152	MPa	ASTM D790

KetaSpire® KT-820FP

polyetheretherketone

Impact	Typical Value	Unit	Test method
Notched Izod Impact	69	J/m	ASTM D256
Unnotched Izod Impact	No Break		ASTM D256

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load 1.8 MPa, Unannealed	162	°C	ASTM D648
Glass Transition Temperature	150	°C	ASTM D3417
Melting Temperature	340	°C	ASTM D3417
CLTE - Flow (-50 to 50°C)	4.3E-5	cm/cm/°C	ASTM E831

Injection Notes

Back Pressure: minimum

Notes

Typical properties: these are not to be construed as specifications.

¹ Quenched

² Crystallized

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2017 Solvay Specialty Polymers. All rights reserved.